

	Ref. STD	Unit of meas.	TECHNICAL SPECIFICATIONS			
Substance	ISO 536	g/m ²	39	41		
Caliper	ISO 534	μm	51	53		
MD Tensile Strength	ISO 1924-1/2	KN/m	3,2	3,4		
CD Tensile Strength	ISO 1924-1/2	KN/m	1,4	1,5		
Tearing strength MD	ISO 1974	mN	170	180		
Tearing strength CD	ISO 1974	mN	170	180		
Cobb 60	ISO 535	g/m ²	15	15		

Tolerances	Ref. STD	Unit of meas.	RANGE			
Substance	ISO 536	g/m ²	37/41	39/43		
Caliper	ISO 534	μm	49/53	51/55		
MD Tensile Strength	ISO 1924-1/2	KN/m	min -15%	min -15%		
CD Tensile Strength	ISO 1924-1/2	KN/m	min -15%	min -15%		
Tearing strength MD	ISO 1974	mN	min -30%	min -30%		
Tearing strength CD	ISO 1974	mN	min -30%	min -30%		
Cobb 60	ISO 535	g/m ²	max 18	max 18		

Notes: GOOD RELEASE PROPERTIES FOR BAKING AND COOKING. EXCELLENT FOR USE SEVERAL TIMES.

Finishing **Machine Finished**

Printing method

Applications

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.