PP Gloss Clear S TC / A292F / GW

MEGA Papiers
Le papier, c'est nous

TECHNICAL SPECIFICATIONS

Facestock

PP Gloss Clear S TC

Description	Clear gloss top-coated BOPP. Good temperature and chemicals resistance. Good moisture barrier properties
Color	Clear
Finish	Gloss
Applications	High quality labelling of cosmetics and toiletries where durability and resistance to moisture and chemicals are required. Also recommended for the labelling of fruits and vegetables.
Printing techniques	Suitable for printing on flexo solvent-base, UV flexo, flexo water-based, hot stamping, conventional offset, offset UV, screen printing, letterpress (conventional and UV).

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m²	52	50.5 - 58.1
Thickness	ISO 534	µm	57	± 10%
Dimensional stability 100ºC 10min MD	ASTM D 1204	%	-3	
Dimensional stability 100ºC 10min CD	ASTM D 1204	%	- 1,5	

Adhesive

A292F

Description	A clear adhesive featuring excellent UV resistance and weatherability. Good adhesion performance, even on apolar substrates. Suitable for contact with dry, moist and fatty foods with a reduction factor of 3.
Shelf life	From the date of manufacture 2 years in 20ºC and RH 50%.

Property	Norm	Units	Value	Tolerance
Adhesion (Peel 180º 20'/stainless steel)	FTM 1	N	10	≥ 8
Tack (Quick Stick stainless steel)	FTM 9	N	9,2	≥ 7,8
Shear (1kg, in²/glass)	FTM 8	hours	50	≥ 25
Minimum labelling temperature		ºC	+5ºC	
Minimum service temperature		ºC	-30ºC	
Maximum service temperature.		ºC	+120ºC	

Liner

Glassine White 62

Description	Super-calendered translucent glassine paper especially designed for automatic labelling applications and photocell dispensing systems. This liner provides good tear resistance and smooth and regular thickness.
Color	White

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m2	57	55.9 - 58.5
Thickness	ISO 534	µm	49	47 - 51

- Values are subject to change without notice. Last updated 01/01/2025.
- The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.