

## PP Gloss White S TC / A292F / GW



Facestock

## PP Gloss White S TC

White gloss top-coated BOPP. Good temperature and chemicals resistance. Good moisture barrier Description properties

Color White Finish Gloss

Applications High quality labelling of cosmetics and toiletries where durability and resistance to moisture and

chemicals are required. Also recommended for the labelling of fruits and vegetables.

Suitable for printing on flexo solvent-base, UV flexo, flexo water-based, hot stamping, Printing techniques conventional offset, offset UV, screen printing, letterpress (conventional and UV).

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m2	55	50.5 - 58.1
Thickness	ISO 534	μm	57	± 10%
Dimensional stability 100°C 10min MD	ASTM D 1204	%	-3	± 3

Adhesive

## A292F

A clear adhesive featuring excellent UV resistance and weatherability. Good adhesion Description performance, even on apolar substrates. Suitable for contact with dry, moist and fatty foods with a reduction factor of 3.

Shelf life From the date of manufacture 2 years in 20°C and RH 50%.

Property	Norm	Units	Value	Tolerance
Adhesion (Peel 180º 20'/stainless steel)	FTM 1	N	10	≥ 8
Tack (Quick Stick stainless steel)	FTM 9	N	9,2	≥ 7,8
Shear (1kg, in²/glass)	FTM 8	hours	50	≥ 25
Minimum labelling temperature		°C	+5°C	
Minimum service temperature		°C	-30°C	
Maximum service temperature.		°C	+120°C	

Liner

## Glassine White 62

Super-calendered translucent glassine paper especially designed for automatic labelling Description applications and photocell dispensing systems. This liner provides good tear resistance and smooth and regular thickness.

Color White

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m2	57	55.9 - 58.5
Thickness	ISO 534	μm	49	47 - 51

Values are subject to change without notice. Last updated 01/01/2025

Our self-adhesive mill is certified to the strictest environmental standards ISO 14001 and EMAS and has successfully completed audits for ISO 50001, ISO 9001 and ISO 45001 certification. Adestor paper products are available with PEFC and FSC® C011032 chain of custody certificates upon request.

The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.