

One-side coated paper

Paper for labels and box wrapping

SPARKLING PREMIUM

	Ref. STD	Unit of meas.	TECHNICAL SPECIFICATIONS			
Substance	ISO 536	g/m ²	70			
Caliper	ISO 534	μm	60			
Smoothness Bekk	ISO 5627	s	2000			
Smoothness Bekk back side	ISO 5627	s	350			
Gloss Gardner	ISO 8254-1	%	69			
Brightness ISO	ISO 2470 (D65)	%	90			
Opacity ISO	ISO 2471	%	90			
MD Tensile Strength	ISO 1924-1/2	KN/m	4			
CD Tensile Strength	ISO 1924-1/2	KN/m	2,5			
Wet Breaking Load MD	ISO 3781	KN/m	1,4			
Wet Breaking Load CD	ISO 3781	KN/m	1,1			
Wet opacity	ISO 2471	%	75			
Cobb 60	ISO 535	g/m ²	17			
Cobb 60 back side	ISO 535	g/m ²	16			
Relative moisture	ISO 287	%	50			

Tolerances	Ref. STD	Unit of meas.	RANGE			
Substance	ISO 536	g/m ²	67/73			
Caliper	ISO 534	μm	56/64			
Smoothness Bekk	ISO 5627	s	1400/2600			
Smoothness Bekk back side	ISO 5627	s	245/455			
Gloss Gardner	ISO 8254-1	%	65/73			
Brightness ISO	ISO 2470 (D65)	%	88/92			
Opacity ISO	ISO 2471	%	88/92			
MD Tensile Strength	ISO 1924-1/2	KN/m	3.4/4.6			
CD Tensile Strength	ISO 1924-1/2	KN/m	2.2/2.8			
Wet Breaking Load MD	ISO 3781	KN/m	1.2/1.6			
Wet Breaking Load CD	ISO 3781	KN/m	0.9/1.2			
Wet opacity	ISO 2471	%	73/77			
Cobb 60	ISO 535	g/m ²	14/20			
Cobb 60 back side	ISO 535	g/m ²	13/19			
Relative moisture	ISO 287	%	45/55			

Notes:

- RESISTANCE TO PENETRATION IN ALKALINE SOLUTION (DIN 16524-6): MAX 50 SEC.
- COME_OFF TIME IN ALKALINE SOLUTION (DIN 16524-6): MAX 80 SEC.
- RESISTANCE TO ALKALINE SOLUTION (DIN 16524-7): MIN 60 MIN.

Finishing **Gloss**
Printing method **Sheet-fed offset - Rotogravure - Flexographic**
Applications

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.